

Akvi Primer TIX

APIBŪDINIMAS

A water-borne acrylate primer.

SAVYBĖS IR PASKIRTIS

- Especially designed for vertical and complex surfaces
- Very easy to sand thus ensuring adhesion of the topcoat. The primer also has good stackability.
- Good filling properties enabling the high-quality look of the final surface
- Suitable for furniture, doors, mouldings and other wooden surfaces in interior premises

TECHNINIAI DUOMENYS

Sausojo likučio tūrio dalis (proc.) 41±2%

Sausojo likučio masės dalis (proc.) 59±2%

Tankis 1.4 kg / l

Rekomenduojamas dangos storis ir teorinė išeiga

Recommended spreading amounts (unthinned)		Theoretical coverage
wet	dry	
80–120 g/m ²	35–50 μm	10–11 m ² /l

Practical coverage depends on the application method, conditions and the shape and roughness of the surface to be treated.

Džiūvimo trukmė

100–120 g/m ² wet film	+23°C	+ 50°C	IRM
Dust dry, after	10–15 min	5–10 min	
Touch dry, after	15–20 min	5–10 min	
Dry to sand, after	20–25 min	5–10 min	1–2 min

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

Blizgumas

Matinis.

Spalva

White

Akvi Primer TIX

NAUDOJIMO INSTRUKCIJA

Paviršiaus paruošimas Remove dust, loose particles and other impurities from the surface. Wood surfaces must be sanded with sandpaper P150–320. Sanding prior to the next application with sandpaper P240–400. All sanding dust must be removed.

Rekomenduojama viršutinio sluoksnio danga Akvi Top DS 25, Diccoplast 30, Luminol 25 N, Luminol SP 25.

Dengimo sąlygos The surface to be treated has to be clean and dry. The moisture content of wood has to be below 20%. During application and drying temperature of the air, substrate and product must be over +18°C and relative humidity of the air below 70%. Good ventilation is required to ensure optimal result. Product can be dried with or without oven.

Dengimas Stir the paint carefully.

For airless spraying, the product is thinned approximately 0–10% to the viscosity 40–80s (DIN4). Recommended nozzle tip is 0.011"–0.015" and pressure 100–160 bar. Spray angle shall be chosen according to the shape of the object.

For air-assisted airless spraying, the product is thinned approximately 0–10% to the viscosity 40–80s (DIN4). Recommended nozzle tip is 0.011"–0.015" and pressure 40–120 bar. Atomising air pressure should be about 1–3 bar. Spray angle shall be chosen according to the shape of the object.

For conventional spraying, the product is thinned approximately 0–10% to the viscosity 40–80s (DIN4). Recommended nozzle tip is 1.4-1.8 mm and pressure 2–3 bar.

Skiedikliai Vandens, Akvi Thinner

Įrangos valymas Water or Akvi Thinner.

LOJ The Volatile Organic Compounds amount is 62 g/litre of paint mixture.

VOC content of the paint mixture (thinned 10% by volume) is 57 g/l.

VOC 2004/42/EC (cat A/d) 130 g/l (2010)

SAUGOS IR SVEIKATOS APSAUGOS ŽENKLINIMAS

Nenaudoti, jeigu neperskaityti ar nesuprasti visi saugos įspėjimai. Smulkesnė informacija apie pavojingą poveikį ir apsaugą nuo jo pateikta saugos duomenų lapuose. Saugos duomenų lapą galima gauti paprašius.

Tik pramoniniam ir profesionaliam naudojimui

Pateikta informacija nėra išsami ir galutinė. Ši informacija paremta laboratoriniais bandymais ir praktine patirtimi. Gaminų kokybę užtikrina ISO 9001 ir ISO 14001 standartų reikalavimus atitinkanti kokybės vadybos sistema. Negalėdami kontroliuoti sąlygų, kuriomis gaminiai naudojami, taip pat veiksnų, turinčių įtakos jų naudojimui, neatsakome už patirtą žalą juos naudojant ne pagal instrukcijas ar paskirtį. Pasilieka teisė keisti pateiktą informaciją be išankstinio pranešimo.

Gaminys skirtas naudoti tik profesionaliai, jį gali naudoti tik specialistai, žinantys, kaip tinkamai jį naudoti, ir turintys jo naudojimo patirties. Aukščiau pateikta informacija yra patarimo pobūdžio. Tiek, kiek leidžia galiojantys įstatymai, mes neprisiimame atsakomybės už sąlygas, kuriomis gaminys yra naudojamas, ir už tai, kaip ir koku tikslu jis yra naudojamas.

Jei ketinate naudoti gaminį kitu tikslu nei čia rekomenduojama ir neturite mūsų raštiško patvirtinimo, kad jis tinkamas taip naudoti, prisiimate visą atsakomybę už galimas pasekmes.