

## Dicco Lasyr

### APIBŪDINIMAS

A solvent-borne semi-transparent stain.

### SAVYBĖS IR PASKIRTIS

- Performs best on wood species such as oak, ash and pine, and on wood with similar structure and grain
- Available in a wide range of pastel colors that show the natural structure of wood. Natural-looking color samples on wood are available by request
- A fast-drying stain for interior use
- Recommended for furniture, doors of kitchen fittings, panels, frames and other wooden surfaces indoors

### TECHNINIAI DUOMENYS

Sausojo likučio tūrio dalis (proc.) about 8–13%

Sausojo likučio masės dalis (proc.) about 10–15%

Tankis 0.85–0.95 kg/l.

Rekomenduojamas dangos storis ir teorinė išeiga

Recommended spreading amounts (unthinned)		Theoretical coverage
wet	dry	
40–100 g/m <sup>2</sup>	6–14µm	10–22 m <sup>2</sup> /l

Practical coverage depends on the application method, conditions and the shape and roughness of the surface to be treated.

Džiūvimo trukmė

60–80 g/m <sup>2</sup>	+20°C	+50°C
Recoatable, after	30min	10min

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation

Spalva

Temaspeed Premium tinting. Interior Wood Stains and Lacquers Colour Card. Other colors by request

# Dicco Lasyr

## NAUDOJIMO INSTRUKCIJA

**Paviršiaus paruošimas** Remove dust, loose particles and other impurities from the surface. Wood surfaces must be sanded with sandpaper P150–320. Sanding prior to the next application with sandpaper P240–400. All sanding dust must be removed.

**Rekomenduojama viršutinio sluoksnio danga** Merit 20, Merit 30, Merit 80, Akvilac FD 25, Akvilac FD-J 10, Akvilac FD-J 25, Akvilac FD-J 35, Akvilac FD 70.

**Dengimo sąlygos** The surface to be treated has to be clean and dry. The moisture content of wood has to be below 20%. During application and drying temperature of the air, substrate and product must be over +18°C and relative humidity of the air below 70%. Good ventilation is required to ensure optimal result. Product can be dried with or without oven.

**Dengimas** Stir the stain carefully before use. Stir also after breaks during working day before continuing the work.

Different application methods and type of wood may cause variations of the colour of the stain. The color and intensity of the stain should be verified before applying.

For conventional spraying, the product is not thinned. Recommended nozzle tip is 1.0–1.6 mm and pressure 1–3 bar.

**Skiedikliai** Thinner 1027, Thinner 1033

**Įrangos valymas** Thinner 1033 or 1027.

**LOJ** The Volatile Organic Compounds amount is 800 g/litre of paint.

Maximum VOC content in ready to use paint (thinned 10% by volume) is 800 g/l.

**SAUGOS IR SVEIKATOS APSAUGOS ŽENKLINIMAS** Nenaudoti, jeigu neperskaityti ar nesuprasti visi saugos įspėjimai. Smulkesnė informacija apie pavojingą poveikį ir apsaugą nuo jo pateikta saugos duomenų lapuose. Saugos duomenų lapą galima gauti paprašius.

### Tik pramoniniam ir profesionaliam naudojimui

Pateikta informacija nėra išsami ir galutinė. Ši informacija paremta laboratoriniais bandymais ir praktine patirtimi. Gaminių kokybę užtikrina ISO 9001 ir ISO 14001 standartų reikalavimus atitinkanti kokybės vadybos sistema. Negalėdami kontroliuoti sąlygų, kuriomis gaminiai naudojami, taip pat veiksnių, turinčių įtakos jų naudojimui, neatsakome už patirtą žalą juos naudojant ne pagal instrukcijas ar paskirtį. Pasilieka teisė keisti pateiktą informaciją be išankstinio pranešimo.

Gaminys skirtas naudoti tik profesionaliai, jį gali naudoti tik specialistai, žinantys, kaip tinkamai jį naudoti, ir turintys jo naudojimo patirties. Aukščiau pateikta informacija yra patariamojo pobūdžio. Tiek, kiek leidžia galiojantys įstatymai, mes neprisiimame atsakomybės už sąlygas, kuriomis gaminys yra naudojamas, ir už tai, kaip ir koku tikslu jis yra naudojamas.

Jei ketinate naudoti gaminį kitu tikslu nei čia rekomenduojama ir neturite mūsų raštiško patvirtinimo, kad jis tinkamas taip naudoti, prisiimate visą atsakomybę už galimas pasekmes.