

Temanyl MS Primer

APIBŪDINIMAS

A one-component modified vinyl primer.

SAVYBĖS IR PASKIRTIS

- Easy to handle in the painting process. Due to its high film-building properties, the paint can be applied in thick layers, thus shortening the application process
- Can be applied at sub-zero temperatures, thus making it suitable for surfaces exposed to marine or industrial climates and mild chemical stress
- Suitable for underwater steel, zinc and aluminium structures, such as boat bottoms. The paint is also used as a primer under conventional and self-polishing antifoulings
- Good abrasion, immersion and atmospheric resistance
- Can also be applied at low temperature conditions
- Suitable to be used as a primer under vinyl, chlorinated rubber and acrylic topcoats
- Suitable for underwater steel, zinc and aluminium structures like ship bottoms etc
- Used also as a primer under conventional and selfpolishing antifoulings

TECHNINIAI DUOMENYS

Sausojo likučio tūrio dalis 38±2% (ISO 3233)
(proc.)

Sausojo likučio masės dalis (proc.) 53±2%

Tankis 1.1 kg / l

Rekomenduojamas dangos storis ir teorinė išeiga

Rekomenduojamas dangos storis		Teorinė išeiga
šlapios	sausos	
160µm	60µm	6.3 m ² /l
265µm	100µm	3.8 m ² /l

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

Džiūvimo trukmė

Sausos dangos storis 80µm	+5°C	+10°C	+23°C	+35°C
Nelimpa dulкės po	2 val.	1½ val.	1 val.	½ val.
Galima dengti kitą sluoksnį po	6 val.	4 val.	3 val.	2 val.

Blizgumas

Matinis.

Spalva

Aluminium (reddish aluminium with Temaspeed Premium tinting).

Temanyl MS Primer

NAUDOJIMO INSTRUKCIJA

Paviršiaus paruošimas	<p>Oil, grease, salts and dirt are removed by appropriate means. (ISO 12944-4)</p> <p>Steel surfaces: Blast clean to grade Sa2½. (ISO 8501-1) If blast cleaning is not possible, phosphating is recommended for cold rolled steel to improve adhesion.</p> <p>Zinc surfaces: Sweep blast clean with mineral abrasives, e.g. quartz sand, to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with Panssaripesu detergent. For hot dip galvanized surfaces see separate application instructions or contact Tikkurila Technical Service.</p> <p>Aluminium surfaces: Sweep blast clean with non-metallic abrasives to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with Maalipesu detergent.</p> <p>Primed surfaces: Oil, grease, salt and dirt are removed from the surface by appropriate means. Repair any damage to the primer coat. Note the overcoating time of primer. (ISO 12944-4)</p>
Rekomenduojamas gruntas	Temanyl MS Primer, Temabond ST 200, Temabond ST 300, Temazinc 77, Temazinc 99.
Rekomenduojama viršutinio sluoksnio danga	Temacryl AR 50, Temachlor 40.
Dengimo sąlygos	<p>All surfaces must be clean, dry and free from contamination. The temperature of the ambient air, surface and paint should not fall below -5°C during application and drying. Relative humidity of the air should not exceed 80% during application and drying. The surface temperature of steel should remain at least 3°C above the dew point. Good ventilation and sufficient air movement is required in confined areas during application and drying.</p>
Dengimas	<p>Stir the product carefully before use.</p> <p>For airless spraying, the product is thinned approximately 0–5%. Recommended nozzle tip is 0.018"–0.023" and pressure 15 MPa (150 bar). Spray angle should be 65°–80°.</p> <p>For brush application the product should be thinned according to the circumstances.</p>
Skiedikliai	Thinner 1006
Įrangos valymas	Thinner 1006.
LOJ	<p>The Volatile Organic Compounds amount is 540 g/litre of paint.</p> <p>VOC content of the paint (thinned 5% by volume) is 557 g/l.</p>
SAUGOS IR SVEIKATOS APSAUGOS ŽENKLINIMAS	<p>Nenaudoti, jeigu neperskaityti ar nesuprasti visi saugos įspėjimai. Smulkesnė informacija apie pavojingą poveikį ir apsaugą nuo jo pateikta saugos duomenų lapuose. Saugos duomenų lapą galima gauti paprašius.</p> <p>Tik pramoniniam naudojimui</p>

Temanyl MS Primer

Pateikta informacija nėra išsami ir galutinė. Ši informacija paremta laboratoriniais bandymais ir praktine patirtimi. Gaminių kokybę užtikrina ISO 9001 ir ISO 14001 standartų reikalavimus atitinkanti kokybės vadybos sistema. Negalėdami kontroliuoti sąlygų, kuriomis gaminiai naudojami, taip pat veiksnių, turinčių įtakos jų naudojimui, neatsakome už patirtą žalą juos naudojant ne pagal instrukcijas ar paskirtį. Pasilieiname teisę keisti pateiktą informaciją be išankstinio pranešimo.

Gaminys skirtas naudoti tik profesionaliai, jį gali naudoti tik specialistai, žinantys, kaip tinkamai jį naudoti, ir turintys jo naudojimo patirties. Aukščiau pateikta informacija yra patarimo pobūdžio. Tiek, kiek leidžia galiojantys įstatymai, mes neprisiimame atsakomybės už sąlygas, kuriomis gaminys yra naudojamas, ir už tai, kaip ir kokiu tikslu jis yra naudojamas.

Jei ketinate naudoti gaminį kitu tikslu nei čia rekomenduojama ir neturite mūsų raštiško patvirtinimo, kad jis tinkamas taip naudoti, prisiimate visą atsakomybę už galimas pasekmes.